



GLASTER

APP Modified Bitumen Membrane

Introduction:

GLASTER membranes are made with a double reinforcement of non woven polyester and fiberglass. The fiberglass is set on top of the polyester to grant better UV resistance and high dimensional stability, when compared to the single reinforced membrane.

GLASTER is recommended in the waterproofing works where severe stress could be present.

Description:

GLASTER membranes 4 or 5 mm thick, are manufactured from bitumen modified with atactic polypropylene (APP). The compound is a mixture of distilled bitumen plastomers and elastomers which gives ultimate elastomeric results and high flexibility at very low temperature of -5°C , and the ability to withstand high temperatures.

Membrane is reinforced by two carrier mats, 180 g/m^2 non-woven polyester and 80 g/m^2 fiberglass. The non-woven fabric gives the superior mechanical resistance to stand fatigue and tear caused by different superficial movements of adjoining layers, while the inorganic reinforcement gives the membrane outstanding dimensional stability.

The underside is finished with burn-off polyethylene film, and the upper side can be either smooth or sand.

Advantages:

- High dimensional stability.
- High resistance to thermal aging.
- High puncture resistance.
- Withstanding extreme temperatures.

Uses:

- To fix the sheet to the substrate, use a propane gas burner to melt off the polyethylene film and a thin layer of bitumen while unrolling and laying the membrane. Side laps 100 mm and end laps 150 mm. Smoothen the overlaps with a hot round-tipped trowel.
- Excessive heating may damage the reinforcement.
- The membrane maybe loosely laid, partially or fully bonded, depending on the structure and the specifications.

Field of Application:

GLASTER membranes are designed for use in heavy duty applications such as underground foundations, basements, retaining walls, tunnels, reservoirs, anti-earthquake foundation, multi-story car parks, etc. And where toughness, dimensional stability and impact resistance are required.



Technical Specifications

Property	Result	Test Method
Dimension, m/roll	1x10	
Thickness, mm	4 or 5	ASTM D5147
Weight per roll, Kg	50 or 62	UEAtc MOAT30
Reinforcement	Nonwoven Polyester 180 g/m ² . Reinforced Fiberglass 80 g/m ² .	BS 747
Penetration at 25°C, dmm	20±10	ASTM D5
Softening point, °C	≥150	ASTM D36
Heat Resistance	No flowing after 2 hours at 100 °C.	UEAtc MOAT30
Cold Pliability	No cracking at -5 °C	UEAtc MOAT27
Tensile Strength, N/5cm	Long. 750 Transv. 600	ASTM D5147 & D146
Ultimate Elongation,%	Long. 35 Transv. 40	ASTM D146
Water Absorption, %.	<1	ASTM D5147
Static Indentation Resistance	Not perforated at 25 kg. (Class L4).	BS 747
Water Pressure Resistance	No leakage at 1000 mm water head/24 hrs.	UEAtc MOAT27
Water Vapor Transmission	0.2 g/m ² per day	ASTM E96
Chemicals Resistance.	Resistant to alcohol, salt solutions, dilute acids and alkalies.	

- This Technical Data is the average results of tests, measurements and trials carried out by LAMA's own laboratory and according to international standards such as ASTM, B.S and UEAtc, Acceptable deviation according to UEAtc.
- This product data sheet supersedes all previous data publications pertaining to this product.
- This data may be changed, improved or modified by LAMA, in accordance with the Client's requirements, availability of raw material, without advance notice.